

**NORTHERN GREECE CERAMICS S.A.**

Nea Santa 61100 - Kilkis, Greece

Tel: 0030 23410 75570

Fax: 0030 23410 75574

Email: info@kebe-sa.gr

web: www.kebe-sa.gr

EST. 1935

KOTHALI**KEBE**

NORTHERN GREECE CERAMICS

12**EN 771-1:2011+A1:2015****Λ No 0****Horizontally Perforated Clay Masonry unit P, for use in protected masonry,
Category II**

DOP Reference No	AN0-25	
Length	190	mm
Width	90	mm
Height	60	mm
Dimentional tolerance	T1	
Range category	R1	
Flatness of bed faces	NPD	
Plane parallelism of bed faces	NPD	
Configuration	As in attached drawing	
Gross dry density	975	kg/m ³
Net dry density	1.775	kg/m ³
Density tolerance	D1:10	%
Mean compressive strength (perpendicular to bed face)	≥3,0	N/mm ²
Category	II	
Bond strength (Tabulated value acc.to EN 998-2 Annex C)	0,15	N/mm ²
Thermal conductivity λ _{eq}	NPD	
Water vapour permeability μ	5/10	
Durability against freeze/thaw	F0	
Water absorption	NPD	
Active soluble salt content	S0	
Reaction to fire : Euroclass	A1	
Dangerous substances	NPD	

Particular conditions applicable to the use: Cutting with power tools may generate dust. This dust will contain silica or quartz particulate which may constitute a hazard. People undertaking works of this nature are advised to wear dust masks FFP3 (EN 149).

