

**NORTHERN GREECE CERAMICS S.A.**

Nea Santa 61100 - Kilkis, Greece

Tel: 0030 23410 75570

Fax: 0030 23410 75574

Email: info@kebe-sa.gr

web: www.kebe-sa.gr

EST. 1935

**KOTHALI****KEBE**

NORTHERN GREECE CERAMICS

**13****EN 771-1:2011+A1:2015****ORTHOBLOCK PLUS K250****Vertically Perforated Clay Masonry unit P, for use in protected masonry, Category II and voids filled with expanded polystyrene (EPS) containing graphite.**

DOP Reference No	PK250-25	
Length	250	mm
Width	250	mm
Height	240	mm
Dimensional tolerance	T1	
Range category	R1	
Flatness of bed faces	≤1	mm
Plane parallelism of bed faces	≤1	mm
Configuration	As in attached drawing	
Gross dry density	800	kg/m <sup>3</sup>
Net dry density	1900	kg/m <sup>3</sup>
Density tolerance	D1:10	%
Mean compressive strength (perpendicular to bed face)	12,0	N/mm <sup>2</sup>
Category	II	
Bond strength (Tabulated value acc.to EN 998-2 Annex C)	0,30	N/mm <sup>2</sup>
Thermal conductivity $\lambda_{10,dry,unit}$ (P3)	0,0901	W/mK
Thermal conductivity $\lambda_{equ,design,masonry}$ (with 3mm mortar joints)	0,1053	W/mK
Water vapour permeability $\mu$	5/10	
Durability	F0	
Water absorption	NPD	
Active soluble salt content	S0	
Reaction to fire - Class	B-s1,d0	
Dangerous substances	NPD	

**Particular conditions applicable to the use:**

Cutting with power tools may generate dust. People undertaking works of this nature are advised to wear suitable personal protective equipment (PPE)

