


# Horizontally Perforated Brick Facing



UNITS /  
PALETTE:  
**512**

 **EPD**<sup>®</sup>  
THE INTERNATIONAL EPD<sup>®</sup> SYSTEM

 **EPD**<sup>®</sup>  
CLIMATE DECLARATION



Horizontally Perforated Clay Brick, for use in protected masonry, category II, certified according to EN 771-1:2011+A1:2015.

## TECHNICAL DATA

Dimensions (LxWxH) (mm)	250x120x60
Weight per Unit (kg/unit)	1,70
Masonry Thickness (mm)	120
Units/m <sup>2</sup>	55
Estimated Masonry Weight (kg/m <sup>2</sup> ) without mortar	55
Gross Dry Density (kg/m <sup>3</sup> )	945
Net Dry Density (kg/m <sup>3</sup> )	1.900
Mean Compressive Strength (perpendicular to bed face) (N/mm <sup>2</sup> )	≥ 7,0
Water Vapour Permeability $\mu$	5 / 10
Durability against freeze/thaw	F0
Reaction to Fire	A1