

Horizontally Perforated Brick AK90



UNITS /
PALETTE:
220

EPD[®]
THE INTERNATIONAL EPD[®] SYSTEM

EPD[®]
CLIMATE DECLARATION



Horizontally Perforated Clay Brick, for use in protected masonry, category II, certified according to EN 771-1:2011+A1:2015.

TECHNICAL DATA

Dimensions (LxWxH) (mm)	230x90x190
Weight per Unit (kg/unit)	3,00
Masonry Thickness (mm)	90
Units/m ²	20
Estimated Masonry Weight (kg/m ²) without mortar	60
Gross Dry Density (kg/m ³)	763
Net Dry Density (kg/m ³)	1.775
Mean Compressive Strength (perpendicular to bed face) (N/mm ²)	≥ 5
Water Vapour Permeability μ	5 / 10
Durability against freeze/thaw	F0
Reaction to Fire	A1