

Horizontally Perforated Brick

ΛΝο0



UNITS /
PALETTE :
770

Horizontally Perforated Clay Brick, for use in protected masonry, category II, certified according to EN 771-1:2011+A1:2015.

TECHNICAL DATA

Dimensions (LxWxH) (mm)	190x60x90
Weight per Unit (kg/unit)	1,00
Masonry Thickness (mm)	60 / 90
Units/m ²	50 / 70
Estimated Masonry Weight (kg/m ²) without mortar	50,00 / 70,00
Gross Dry Density (kg/m ³)	975
Net Dry Density (kg/m ³)	1.775
Mean Compressive Strength (perpendicular to bed face) (N/mm ²)	≥ 3
Water Vapour Permeability μ	5 / 10
Durability against freeze/thaw	F0
Reaction to Fire	A1