

Horizontally Perforated Brick ΛNo1



UNITS /
PALETTE:
525

EPD[®]
THE INTERNATIONAL EPD[®] SYSTEM

EPD[®]
CLIMATE DECLARATION



Horizontally Perforated Clay Brick, for use in protected masonry, category II, certified according to EN 771-1:2011+A1:2015.

TECHNICAL DATA

Dimensions (LxWxH) (mm)	190x90x90
Weight per Unit (kg/unit)	1,30
Masonry Thickness (mm)	90
Units/m ²	50
Estimated Masonry Weight (kg/m ²) without mortar	65,00
Gross Dry Density (kg/m ³)	845
Net Dry Density (kg/m ³)	1.775
Mean Compressive Strength (perpendicular to bed face) (N/mm ²)	≥ 3
Water Vapour Permeability μ	5 / 10
Durability against freeze/thaw	F0
Reaction to Fire	A1