

Horizontally Perforated Brick No0



UNITS /
PALETTE:
900



Horizontally Perforated Clay Brick, for use in protected masonry, category II, certified according to EN 771-1:2011+A1:2015.

TECHNICAL DATA

Dimensions (LxWxH) (mm)	190x60x90
Weight per Unit (kg/unit)	0,90
Masonry Thickness (mm)	60/90
Units/m ²	50/70
Estimated Masonry Weight (kg/m ²) without mortar	45/63
Gross Dry Density (kg/m ³)	880
Net Dry Density (kg/m ³)	1.900
Mean Compressive Strength (perpendicular to bed face) (N/mm ²)	≥ 2,5
Water Vapour Permeability μ	5 / 10
Durability against freeze/thaw	F0
Reaction to Fire	A1