

# ORTHOBLOCK<sup>®</sup> PLUS

## NK300



UNITS /  
PALETTE:  
48

 EPD<sup>®</sup>  
THE INTERNATIONAL EPD<sup>®</sup> SYSTEM

 EPD<sup>®</sup>  
CLIMATE DECLARATION



Vertically Perforated Clay Brick, for use in protected masonry, Category II, certified according to EN 771-1:2011+A1:2015.

### TECHNICAL DATA

Masonry	Non-Load Bearing
Dimensions (LxWxH) (mm)	250x300x240
Weight per Unit (kg/unit)	13,15
Masonry Thickness (mm)	300
Units/m <sup>2</sup>	16
Estimated Masonry Weight (kg/m <sup>2</sup> ) without mortar	210,40
Gross Dry Density (kg/m <sup>3</sup> )	720
Net Dry Density (kg/m <sup>3</sup> )	1.900
Mean Compressive Strength (perpendicular to bed face) (N/mm <sup>2</sup> )	9
Thermal Conductivity Coefficient $\lambda_{10,dry,unit}$ (W/mK)	0,0839
Thermal Design Conductivity Coefficient $\lambda_{equ,design,masonry}$ (with 3mm ORTHOBLOCK BOND) (W/mK)	0,0985
Thermal Transmittance $U_{w,design}$ without any plaster (with 3mm ORTHOBLOCK BOND) (W/m <sup>2</sup> K)	0,3110
Sound Reduction Index $R_w$ (dB)	52 **
Water Vapour Permeability $\mu$	5 / 10
Durability against freeze/thaw	F0
Reaction to Fire	B-S1, d0

\* The above coverage of **OPΘOBLOCK BOND** is indicative and it is the result of laboratory and on site measurements. It includes only horizontal joints 3mm thick (vertical joints in non-load bearing masonries built with **OPΘOBLOCK** are not required).


\*\* Calculated Measurement

### SUPPLEMENTARY PRODUCTS



**BONDING MORTAR**  
**OPΘOBLOCK BOND**  
(paper bag of 25kg)

Coverage:  
2,0-3,5 m<sup>2</sup> masonry per bag \*



**METAL LINTEL**

Unit's Width: 30cm